



International Polyurethane Systems Inc.

P.O. Box 3309 * 5590 - 46th Ave. SE
Salmon Arm, B.C. V1E 4S1 * Canada

Tel 250-832-5142 Fax 250-832-9338

Material Data Sheet Binder D1010/9

Product Description:

A low viscosity, one component polyurethane binder based on aromatic MDI which does not contain any solvent, and cures by reaction with atmospheric moisture. Typical uses are pour-in place applications.

Chemical Properties:

Properties	Unit	Test Method	Typical Values
Appearance			clear/amber
Isocyanate Content	%	ASTM D2572-87	11
Density	g/cm ³	ASTM-D 1475	1.10 - 1.15
Viscosity @ 22°C (Brookfield DV-2+ @ 20RPM Spindle 3)	cP	ASTM-D 4878	3500 - 4500
Flash Point	°C		>200

Curing Profile:

Curing takes place by reaction with atmospheric moisture. Curing will be faster at elevated temperatures or with use of catalysts, as well as at higher humidity levels.

Curetime @ 25C (1mm thickness): Approximately 12 - 24 hours

Application:

Apply as needed by mixing with particulate matter. Clean up tools with MEK or xylene.

Storage:

The materials must be protected against humidity and stored at 18 - 25 °C (65 - 77 °F) for optimum shelf life of 6 months.

Disclaimer: Other than as expressly stated in IPS's Terms and Conditions of Sale governing the sale of this material, the information enclosed is given without warranty, representation, or license of any kind. The relationship between the Purchaser and IPS, with regard to this material, is governed exclusively by IPS's Terms and Conditions of Sale. The conditions of your use and the suitability of IPS's products and technical assistance concerning suggested formulations, processing techniques, substrate suitability, etc. are beyond IPS's control. Therefore, it is imperative that you test IPS's products under your own processing conditions to determine to your own satisfaction whether they are suitable for your intended uses and applications.

Revision date: July 7/06